Technical data

## **OptiPro**

## **Industrial Grade Soda Ash**

CAS No. 497-19-8

Chemical Na	me	Sodium Carbonate, anhydrous	
CAS Name		Disodium carbonate	
Formula		Na <sub>2</sub> CO <sub>3</sub>	
Molecular We	eight	105.99	
Physical Prop	perties		
		Typical Range	
Bulk Density:	lb/ft <sup>3</sup>	43 - 52	
	g/cm <sup>3</sup>	0.69 - 0.83	
Screen analys	is, cumulative wt %		
On	US 40 (425 μm)	5 - 35	
	US 100 (150 μm)	65 - 90	
Thru	US 200 (75 μm)	0 - 10	

Chemical Properties				
·	Typical	Specification		
Na <sub>2</sub> O, wt %	58.2	57.9 min		
Na <sub>2</sub> CO <sub>3</sub> , wt %	99.5	99.0 min		
Na <sub>2</sub> SO <sub>4</sub> , %	0.04	0.10 max		
NaCl, %	0.03	0.10 max		
Fe <sub>2</sub> O <sub>3</sub> , ppm	7	20 max		

## **General Properties**

Description	white granular solid
Melting point, °C (°F)	851 (1564)
Solubility, max % @ 35.4°C	33.2
pH, 1% solution @ 25°C	11.4

## **Standard Containers**

Bulk hopper cars and trucks

The information contained herein is, to our knowledge, true and accurate. Because conditions of use are beyond our control, we make no warranty or representation, expressed or implied, except that the products discussed herein conform to the chemical descriptions shown on their labels. Nothing contained herein should be construed as permission or recommendation to infringe any patent. No agent, representative, or employee of this company is authorized to vary any of the terms of this notice.

**Tronox Alkali Corporation** 

1735 Market Street

Philadelphia Pennsylvania 19103